

TextileGarden.

Coffee grounds buttons

Technical info' - in conformity with OEKO-TEX

Coffee grounds	15 - 25%
Recycled fillers (thermosetting)	40 - 50%
Bio polyester resin	30 - 40%
Plasticisers and dyes	2 - 5%

Dye stuff used in this product does not release aromatic amines regarded as forbidden by German law. Different shades of colour are due to the biodegradable component of the product

Resistance to washing max 60 deg
I have tested at 30 degrees in a washing machine on a regular programme and the buttons were fine. I would recommend a 30 degree wash

Resistance to ironing max 110 deg

Resistance to dry cleaning Yes

Resistance to steam ironing Yes

Dyeable No

Resistance to tensile strength on the holes

L20 - 15kg	L24 - 18kg	L32 - 20kg
L36 - 23kg	L40 - 28kg	

Tensile strength changes according to the shape