

TextileGarden.

Eco imitation horn buttons

Buttons manufactured using urea & potato flour. Urea is used to achieve the scorched edge.

Technical info' - in conformity with OEKO-TEX

Urea resin	30 - 40%
Technical binders	35 - 45%
Potato flour	15 - 25%
Dyes	5 - 10%

Dye stuff used in this product does not release aromatic amines regarded as forbidden by German law.

#

Resistance to washing Tmax = 60 deg

Resistance to ironing Tmax = 110 deg

Resistance to dry cleaning Yes

Resistance to steam ironing Yes

Dyeable No

Resistance to tensile strength on the holes

L24 (15mm) - 23kg

L32 (20mm) - 26kg

L40 (25mm) - 36kg

Tensile strength changes according to the shape